

LADLE SHROUDS

	22-04-03	22-04-01	22-04-02
Plain Carbon	X	X	
Al Killed		X	X
Ca Treated	X		
Stainless	X	X	
High Mn	X		
Al ₂ O ₃ , % Min	55	48	45
SiO ₂ , % Max	9	15	26
Carbon, % Min	34	35	28
Apparent Porosity, % Max	12	14	15
Bulk Density, g/cm ³ Min	2.4	2.3	2.28
Cold Crushing Strength, Kg/cm ² , Min	200	200	190

The above data are typical properties. The data is subject to reasonable variations in manufacturing and should not be used for specification purposes.