

METALLURGICAL AND FOUNDRY GRADE COKE

	Foundry Coke	Metallurgical Coke	Metallurgical Coke	Metallurgical Coke
	FC 125	MC 126	MC 127	MC 128
Moisture	5% max	5% max	5% max	5% max
Ash	10.5% max	12% max	12% max	10% max
Sulphur	0.6% max		0.6% max	0.6% max
V.M.	1.5% max	1.5% max	1.5%	1.4%
Phos.	0.03% max	0.03% max	0.03% max	0.03% max
FC	88% min			
Total Heat	13,000 – 15,000 BTU			
Size: < 100 mm	12% max			
Size: > 300 mm	5% max			
M40	84% min	80% min	80% min	82% min
M10	7% max	9% max	9% max	8% max
CSR	63% min	60% min	60% min	60% min
CRI	26% max	28% max	26% max	26% max
Package	Bulk or super sack	Bulk	Bulk	Bulk
Size	100-300 mm or 30-100mm	30-80 mm	30 – 90 mm	30 – 90 mm

The above data are typical properties. The data is subject to reasonable variations in manufacturing and should not be used for specification purposes.