

STOPPER RODS

PRODUCT NAME	22-02-01	22-02-05	22-02-06	22-02-04	22-02-03	22-02-02
APPLICATION	Body		Nose			
Plain Carbon Normal Grades	x	X				
AK Grades	x	x	X			
Ca Treated	X				X	
Stainless	X		X	X		X
High Manganese	X		x			
Al ₂ O ₃ , % Min	48	70	78	62		60
SiO ₂ , % Max	16	5	5	8		6
MgO, % Min					75	
ZrO ₂ , % Min						4
C, % Min	35	20	17	22	21	22
Apparent Porosity, % Max	15	15	15	13	17	15
Bulk Density, g/cm ³ Min	2.41	2.65	2.68	2.70	2.60	2.70
Cold Crushing Strength, Kg/cm ² , Min	200	250	260	215	210	225

The above data are typical properties. The data is subject to reasonable variations in manufacturing and should not be used for specification purposes.