

ULTRADOL FIRED MAGNESIA / DOLOMITE BRICK

PRODUCT NAME	ULTRADOL 20A	ULTRADOL 30A
MgO	75.68	65.73
CaO	19.91	30.83
Fe ₂ O ₃	0.64	0.59
SiO ₂	1.42	0.96
Al ₂ O ₃	0.66	0.41
Apparent Porosity, %	5.00	5.20
Bulk Density, g/cm ³	3.13	3.10
Cold Crushing Strength	112	139
Refractoriness Under Load	1700	1700

The above data are typical properties. The data is subject to reasonable variations in manufacturing and should not be used for specification purposes.